



Mr P Sykes
 Breedon Southern Ltd
 Cloud Hill Quarry
 Breedon on the Hill
 Derby

01332 694010

GRADATION ANALYSIS TEST REPORT
for Product: BR006014/ 6.3/14mm S/S Buff
Supplier/ source: Breedon Aggregates, Breedon

Material type: Proprietary Specification Test method: Wash grading to BS EN 933-1:1997

SAMPLE INFORMATION

Sample number EJBR01703
 Quarry Production -
 Ticket/truck number -
 Sampling notes -
 Remarks 1 -

Chainage/layer -
 Weather conditions -
 Aggregate type -
 Remarks 2 -

Sampled/ tested
 Tue 01 August 2017/ 03-08-17
 at 1021 hrs


SAMPLE ANALYSIS


Sieve size	Percent passing	Specification limits	Complies ?
31.5mm	100	100 - 100	yes
25mm	100	-	-
20mm	99	98 - 100	yes
16mm	99	-	-
14mm	98	85 - 100	yes
12.5mm	72	-	-
10mm	11	-	-
8mm	1	-	-
6.3mm	1	0 - 20	yes
5mm	1	-	-
4mm	1	-	-
2.8mm	1	-	-
2mm	1	-	-
0.063mm	1	0 - 5	yes
Moisture content %	1.0	not specified	-
Nominal size(14 - 10mm)	87	=>65	yes

Parameters are evaluated to the accuracy of spec. limits

REMARKS

Compliance status ok
 Category A of A-C includes secondary parameters



Signed  for MLTS/ for Client Date 24/8 /2017
 P Sykes, Technical Manager