



Technical Manager (North)
Technical Services
Clatchard Laboratory
Clatchard Quarry
Cupar Road
Newburgh, Fife, KY146JJ
01337 840461

PSD Single Sized Products

GRADATION ANALYSIS TEST REPORT
for Product: 1200/ 10/20 Coarse Aggregate
Supplier/ source: DRY 406 Banavie

Material type: PD6682-2 Table 3 Go85/20 Test method: Dry grading to BS EN 933-1:2012

SAMPLE INFORMATION

Sample number	BEN_01807_B		Sampled/ tested
Customer	Breedon Aggregates	Full Destination	Wed 03 June 2015/ 16-06-15
Ticket <> Truck Reg	-	SampCert <> Chainage	at 1507 hrs
Sampled by<>Operator	K Smith<>G Melvin/K SMith	Weather Conditions	
Retest Samp Nos Data	-	Logged by	O-Cast/Mild/Calm G Melvin
		Stock	

SAMPLE ANALYSIS

Sieve size	Percent passing	Specification limits
40mm	100	100 - 100
31.5mm	100	98 - 100
25mm	100	-
20mm	98	85 - 99
16mm	52	-
14mm	32	-
12.5mm	15	-
10mm	3	0 - 20
8mm	1	-
6.3mm	1	-
5mm	1	-
4mm	1	0 - 5
500µm	1	-
63µm	0	-
Moisture content %	0.3	not specified
Flakiness index	6	<=35

Parameters are evaluated to the accuracy of spec. limits

REMARKS

Signed _____ Technical Manager

Print date 27 Aug 2015