BREEDON AGGREGATES

PSD Single Sized Products

Technical Manager (North)
Technical Services
Clatchard Laboratory
Clatchard Quarry
Cupar Road
Newburgh, Fife, KY146JJ
01337 840461

GRADATION ANALYSIS TEST REPORT
for Product: 1200/ 10/20mm Coarse Aggregate
Supplier/ source: DRY 572 Craigenlow

Material type: Drystone aggregate Test method: Wash grading to BS EN 933-1:2012

SAMPLE INFORMATION

Sampled/ tested
Tue 04 August 2015/ 11-08-15
at 0930 hrs

Sample number	**TOM_01694_A**		
Customer	BASL PRODUCTION	Full Destination	CRAIGENLOW STOCK
Ticket <> Truck Reg	-	SampCert <> Chainage	103526<>
Sampled by<>Operator	D.MCRAE<>	Weather Conditions	DRY,BRIGHT,COOL,STILL
Retest Samp Nos Data	-	Logged by	D.MCRAE

SAMPLE ANALYSIS

Sieve size	Percent passing	Specification limits
40mm	100	100 - 100
31.5mm	100	98 - 100
25mm	100	-
20mm	94	85 - 100
16mm	67	-
14mm	45	-
12.5mm	27	-
10mm	6	0 - 20
8mm	2	-
6.3mm	1	-
5mm	1	-
4mm	1	0 - 5
2.8mm	1	-
2mm	1	-
1mm	1	-
500µm	1	-
63µm	1	0 - 4
Moisture content %	0.4	not specified
Flakiness index	10	<=35

Parameters are evaluated to the accuracy of spec. limits

REMARKS

Signed _____ Technical Manager

Print date 27 Aug 2015

Gradlab GDS v7.11 © Hugh Lerwill www.gradlab.com. Licence#: THL04/230 for Breedon Aggregates (Scotland) Ltd, Site/user name: Clatchard 2.