

Additional information and clarification of content should be directed to the
Technical Services Department either by:

Telephone: 01337 840461

Email: technical.services@breedonaggregates.com



Technical Services Dept

Clatchard Laboratory

Clatchard Quarry

Cupar Road

Newburgh

Fife, KY14 6JJ

Tel: 01337 840461

Fax: 01337 841990

CRAIGENLOW QUARRY

Dunecht

Skene

Aberdeenshire

AB32 7ED

01330 833361

Date Sampled	Property	Specification	Result	Unit
11/02/2015	Particle Density & Absorption (<i>PD&A</i>)	BS EN 1097-6		
	Apparent Density (<i>A</i>)		2.67	Mg/m ³
	Oven Dried Density (<i>OD</i>)		2.62	Mg/m ³
	Saturated Surface Dry Density (<i>SSD</i>)		2.64	Mg/m ³
	Water Absorption (<i>WA</i>)		0.7	%
01/04/2014	Polished Stone Value (<i>PSV</i>)	BS EN 1097: Part 8	55	Value
17/01/2013	Polished Stone Value (<i>PSV</i>)	BS EN 1097: Part 8	57	Value
24/10/2011	Polished Stone Value (<i>PSV</i>)	BS EN 1097: Part 8	57	Value
11/02/2015	Aggregate Abrasion Value (<i>AAV</i>)	BS EN 1097: Part 8	4.9	Value
11/02/2015	Magnesium Sulphate Soundness Value (<i>MSSV</i>)	BS EN 1367: Part 2	7	%
20/07/2015	Los Angeles Coefficient Value (<i>LA</i>)	BS EN 1097: Part 2	33	%
	Los Angeles Coefficient Value (<i>LA - Rail Ballast</i>)	BS EN 1097: Part 2		%
11/02/2015	Micro Deval (<i>MD - Aggregate</i>)	BS EN 1097: Part 1	9	Value
	Micro Deval (<i>MD - Rail Ballast</i>)	BS EN 1097: Part 1		Value
28/08/2012	Alkali Silica Reactivity (<i>ASR</i>)	BS 812: 104 & BS EN 932: 3	Low	n/a
11/02/2015	Drying Shrinkage Value (<i>Dshrink</i>)	BS EN 1367: Part 4	0.013	%
	Linear Coefficient of Thermal Expansion (<i>LCoTE</i>)	3PC/06/01		mm/°C
03/06/2014	Frost Heave (<i>FH - Type I Sub-Base</i>)	BS 812: Part 124	7.5	mm
03/06/2014	Plasticity	BS 1377: Part 2	NP	n/a
11/02/2015	Frost Heave (<i>FH - Recycled Type I Sub-Base</i>)	BS 812: Part 124	11.3	mm
11/02/2015	Plasticity	BS 1377: Part 2	NP	n/a
11/02/2015	Potential Hydrogen Value (<i>pH</i>)	BS 1377: Part 3	8.6	Value
11/02/2015	Total Potential Sulphate Content	TRL Report 447 Test No. 4	<0.03	%
11/02/2015	Oxidisable Sulphides Content (<i>as OS</i>)	TRL Report 447 Test No. 2 & 4	<0.01	%
11/02/2015	Total Sulphur Content (<i>as S</i>)	BS EN 1744: Part 1	<0.1	%
11/02/2015	Soluble Sulphate Content (Water) (<i>as SO₃</i>)	BS EN 1744: Part 1	<0.01	%
11/02/2015	Soluble Sulphate Content (Water) (<i>as SO₄</i>)	BS EN 1744: Part 1	<0.01	%
	Soluble Sulphate Content (Acid)	BS EN 1744: Part 1		%
11/02/2015	Sulphide Content (<i>as S</i>)	BS EN 1744: Part 1	0.21	%
11/02/2015	Chloride Content (<i>as C</i>)	BS EN 1744: Part 1	<0.001	%
11/02/2015	Calcium Carbonate Content (<i>as CaCO₃</i>)	BS EN 196: Part 2	1	%
	Total Neutralising Value (<i>TNV</i>)	BS 6463: Part 2		%