Material Type: (3) Drystone aggregate

154C527/ 10/20mm Gc85-20 Hardstone from 154/Criggion Quarry to Job 100 General

Last 12 or all ending 28437, Samples searched 27754 - 28437 (30-Sep-15 to 18-Dec-15 Last) sorted by Date Sampled

Sample no.	Seq no.	Date sampled	40mm % pass	31.5mm % pass	20mm % pass	14mm % pass	10mm % pass	4mm % pass	0.063mm % pass	Moisture content%	Flaki. index	Compliance status	Category A-C inc2nd
27754	1	30 Sep 15 07:50	100	100	97	10	0	0	0	0.8	-	ok	A
27820	2	08 Oct 15 08:50	100	100	95	4	1	1	0	0.8	2	ok	A
27903	3	16 Oct 15 11:10	100	100	90	5	0	0	0	1.0	-	ok	A
27951	4	22 Oct 15 10:40	100	100	96	9	1	0	0	0.7	-	ok	A
27979	5	27 Oct 15 13:10	100	100	95	14	1	1	0	1.3	-	ok	A
28069	6	04 Nov 15 11:50	100	100	96	11	0	0	0	1.0	-	ok	A
28104	7	10 Nov 15 11:20	100	100	99	18	1	1	0	0.8	3	ok	A
28186	8	18 Nov 15 12:35	100	100	99	23	1	0	0	1.2	-	ok	A
28256	9	26 Nov 15 12:10	100	100	99	9	1	0	0	1.1	-	ok	A
28298	10	02 Dec 15 14:40	100	100	96	6	1	0	0	1.3	-	ok	A
28369	11	09 Dec 15 13:00	100	100	98	13	1	0	0	1.2	-	ok	A
28417	12	17 Dec 15 08:35	100	100	98	18	1	0	0	0.7	11	ok	A
			40mm	31.5mm	20mm	14mm	10mm	4mm	0.063mm	Moisture	Flaki.		
			% pass	% pass	% pass	% pass	% pass	% pass	% pass	content%	index		
Spec Min		**low**	**100**	**98**	**85**	**spacer**	**0**	**0**	**0**	**-**	**0**		
Spec Max		**high**	**100**	**100**	**100**	**spacer**	**20**	**5**	**4**	**-**	**20**		
Average			100.0	100.0	96.5	11.7	0.8	0.3	0.0	0.99	5.3		
n results			12	12	12	12	12	12	12	12	3		
% in-spec			100	100	100	-	100	100	100	-	100		
Cat As	12	100.0%											
Cat Bs	0	0.0%											
Cat Cs	0	0.0%											
Total	12	categorised											