



Technical Manager (North)  
Technical Services  
Clatchard Laboratory  
Clatchard Quarry  
Cupar Road  
Newburgh, Fife, KY146JJ  
01337 840461

PSD Single Sized Products

**GRADATION ANALYSIS TEST REPORT**  
**for Product: 1200/ 10/20 Coarse Aggregate**  
**Supplier/ source: DRY 509 Shierglas**

Material type: PD6682-2 Table 3 Gc85/20 Test method: Wash grading to BS EN 933-1:2012

SAMPLE INFORMATION

Sampled/ tested  
Tue 26 May 2015/ 26 05 15  
at 0820 hrs

<b>Sample number</b>	<b>CLA_07955_F</b>		
Customer	BASL Production	Full Destination	Stock
Ticket <> Truck Reg	-	SampCert <> Chainage	102998<>
Sampled by<>Operator	D O'Byrne	Weather Conditions	Cloudy Cold Dry Still
Retest Samp Nos Data	-	Logged by	D O'Byrne

SAMPLE ANALYSIS

Sieve size	Percent passing	Specification limits
40mm	100	100 - 100
31.5mm	100	98 - 100
25mm	100	-
20mm	97	85 - 99
16mm	64	-
14mm	27	-
12.5mm	8	-
10mm	1	0 - 20
8mm	1	-
6.3mm	1	-
5mm	1	-
4mm	1	0 - 5
500µm	1	-
63µm	1	-
Moisture content %	0.2	not specified
Flakiness index	11	<=35

Parameters are evaluated to the accuracy of spec. limits

REMARKS

---

---

---

---

---

---

---

---

Signed \_\_\_\_\_ Technical Manager

Print date 27 Aug 2015