



PSD Single Sized Products

Technical Manager (North)
Technical Services
Clatchard Laboratory
Clatchard Quarry
Cupar Road
Newburgh, Fife, KY146JJ
01337 840461

GRADATION ANALYSIS TEST REPORT
for Product: 1200/ 10/20mm Coarse Aggregate

Supplier/ source: DRY 575 Stirlinghill
Material type: Drystone aggregate Test method: Wash grading to BS EN 933-1:2012

SAMPLE INFORMATION

Sampled/ tested

Tue 21 July 2015/ 23-07-15
at 1100 hrs

Sample number	TOM_01650_A		
Customer	BASL PRODUCTION	Full Destination	STIRLINGHILL STOCK
Ticket <> Truck Reg	-	SampCert <> Chainage	104044<>
Sampled by<>Operator	D.MCRAE<>	Weather Conditions	DRY,BRIGHT,WARM,STILL
Retest Samp Nos Data	-	Logged by	D.MCRAE

SAMPLE ANALYSIS

Sieve size	Percent passing	Specification limits
40mm	100	100 - 100
31.5mm	100	98 - 100
25mm	100	-
20mm	86	85 - 100
16mm	38	-
14mm	21	-
12.5mm	9	-
10mm	4	0 - 20
8mm	3	-
6.3mm	3	-
5mm	3	-
4mm	3	0 - 5
2.8mm	3	-
2mm	3	-
1mm	3	-
500µm	2	-
63µm	2	0 - 4
Moisture content %	1.2	not specified
Flakiness index	5	<=35

Parameters are evaluated to the accuracy of spec. limits

REMARKS

Signed _____ Technical Manager

Print date 27 Aug 2015