



David P Hynd
 Technical Services Department
 Clatchard laboratory
 Clatchard Quarry
 Cupar Road, Newburgh
 Fife, KY14 6JJ
 01337 840461

PSD Single Sized Products

GRADATION ANALYSIS TEST REPORT
for Product: 1200/ 10/20 Coarse Aggregate

Supplier/ source: DRY 569 Orrock

Material type: PD6682-2 Table 3 Gc85/20 Test method Wash grading to BS EN 933-1 2012

SAMPLE INFORMATION

Sampled/ tested

Thu 28 March 2019/ 28 03 19
 at 0840 hrs

Sample number	CLA_21190_F		
Customer	BGNL Production	Full Destination	Stock - Orrock
Ticket <> Truck Reg	-	SampCert <> Chainage	131444<>
Sampled by<>Operator	T Swan<>	Weather Conditions	Cloud Cold Breeze Dry
Retest Samp Nos Data	-	Logged by	T. Swan


SAMPLE ANALYSIS

Sieve size	Percent passing	Specification limits	Complies ?
40mm	100	100 - 100	yes
31.5mm	100	98 - 100	yes
25mm	100	-	-
20mm	99	85 - 99	yes
16mm	38	-	-
14mm	16	-	-
12.5mm	5	-	-
10mm	1	0 - 20	yes
8mm	1	-	-
6.3mm	1	-	-
5mm	1	-	-
4mm	1	0 - 5	yes
500µm	0	-	-
63µm	0	-	-
Moisture content %	2.0	not specified	-
Flakiness index	10	<=35	yes

Parameters are evaluated to the accuracy of spec limits

REMARKS

Compliance status ok
 Category A of A-C excludes secondary parameters



Signed *[Signature]* Technical Supervisor

Print date 07 May 2019