



James Woods
 Technical Services Department
 Toms Forest laboratory
 Toms Forest Quarry
 Kintore Inverurie
 Aberdeenshire: AB51 0YU

GRADATION ANALYSIS TEST REPORT
for Product: 1200/ 10/20mm Coarse Aggregate
Supplier/ source: DRY

Material type: Drystone aggregate Test method: Wash grading to BS EN 933-1:2012

SAMPLE INFORMATION

Sample number TOM_11034_A
 Customer BNL PRODUCTION Full Destination
 Ticket <> Truck Reg - SampCert <> Chainage 164616
 Sampled by<>Operator Kim Jamieson Weather Conditions DAMP STILL BRIGHT COOL
 Retest Samp Nos Data - Logged by D.MCRAE

Sampled/ tested
 Wed 06 December 2023/ 08 12 23
 at 1310 hrs


SAMPLE ANALYSIS

Sieve size	Percent passing	Specification limits	Complies ?
40mm	100	100 - 100	yes
31.5mm	100	98 - 100	yes
25mm	100	-	-
20mm	96	85 - 99	yes
16mm	52	-	-
14mm	29	-	-
12.5mm	18	-	-
10mm	8	0 - 20	yes
8mm	6	-	-
6.3mm	5	-	-
5mm	5	-	-
4mm	4	0 - 5	yes
2.8mm	4	-	-
2mm	4	-	-
1mm	3	-	-
500µm	3	-	-
63µm	2	-	-
Moisture content %	2.4	not specified	-
Flakiness index	1	<=25	yes

Parameters are evaluated to the accuracy of spec. limits

REMARKS

Compliance status ok
 Category A of A-C excludes secondary parameters



Signed D. McRae Senior Technician

Print date 19 Jan 2024