


# GRADATION ANALYSIS TEST REPORT

Product: 10/20mm Coarse Agg  
 Material Code: A00HS20SS005  
 Supplied by:  
 Customer:  
 Site Address:  
 Material type: BS EN 13043 Table 3 / .  
 Sampled to: BS EN 932 - 1:1997  
 Prepared to: BS EN 933-2 :1999  
 Test method: BS EN 933-1 :2012



BTL Clatchard Laboratory  
 Newburgh Fife  
 KY14 6JJ -

Sample number: 6790  
 Ticket No:  
 Sampled by:  
 Date Sampled: 08/12/2023  
 Sample location: Stockpile  
 Weather Conditions: cold wind wet cloudy  
 Remarks:



| Sieve Size (mm)        | Percent passing | Specification | Complies (Spec) | Control limits | Complies (Ctrl) |
|------------------------|-----------------|---------------|-----------------|----------------|-----------------|
| 40                     | 100             | 100           | Yes             | -              | -               |
| 31.5                   | 100             | 98 - 100      | Yes             | -              | -               |
| 25                     | 100             | -             | -               | -              | -               |
| 20                     | 95              | 85 - 99       | Yes             | -              | -               |
| 16                     | 39              | -             | -               | -              | -               |
| 14                     | 13              | -             | -               | -              | -               |
| 12.5                   | 4               | -             | -               | -              | -               |
| 10                     | 1               | 0 - 20        | Yes             | -              | -               |
| 8                      | 1               | -             | -               | -              | -               |
| 6.3                    | 1               | -             | -               | -              | -               |
| 5                      | 1               | -             | -               | -              | -               |
| 4                      | 1               | 0 - 5         | Yes             | -              | -               |
| 2                      | 1               | -             | -               | -              | -               |
| 0.063                  | 0.7             | 0 - 4.0       | Yes             | -              | -               |
| Moisture content (%)   | 0.2             |               |                 |                |                 |
| Uniformity Coefficient | 1               |               |                 |                |                 |
| Flakiness Index        | 7               | 0 - 30        |                 |                |                 |

Sampled By:

Tested By:

M. Dargie

Date Tested:

12/12/2023