


# GRADATION ANALYSIS TEST REPORT

**Product:** Type B Filter Media  
**Material Code:** Type B FM  
**Supplied by:** Ffestiniog Quarry  
**Customer:**  
**Site Address:**  
**Material type:** SHW Series 505 / Slate  
  
**Test method:** BS EN 933-1:2012



Sample number	38633
Ticket No	
Sampled by	
Date Sampled	11/07/2024
Sample location	
Weather Conditions	



Sieve Size (mm)	Percent passing	Specification	Complies (Spec)	Control limits	Complies (Ctrl)
80		-	-	-	-
63	100	100 - 100	Yes	-	-
50	100	98 - 100	Yes	-	-
40	95	80 - 100	Yes	-	-
31.5	78	-	-	-	-
25	78	-	-	-	-
20	27	0 - 20	No	-	-
16	15	-	-	-	-
14	12	-	-	-	-
12.5	10	-	-	-	-
10	8	0 - 5	No	-	-
4	6	-	-	-	-
2	5	-	-	-	-
0.063	0.3	-	-	-	-
Moisture content (%)	2.0				
Uniformity Coefficient	2				

Sampled By:

Tested By:

Date Tested:

12/07/2024