

Welsh Slate & Aggregates
 Penrhyn Quarry
 Bethesda
 Bangor
 Gwynedd
 LL57 4YG

Date: 14 January 2024
 Test Report Ref: TR 1003387

Contract: Ffestiniog Quarry

LABORATORY TEST REPORT


TEST REQUIREMENTS:

To determine the Particle Size Distribution (PSD) of a aggregate sample-washing and sieving method in accordance with **BS EN 933-1: 2012**.

SAMPLE DETAILS:

Certificate of sampling received:	No	Name of Source:	Ffestiniog
Laboratory Ref. No:	S117061	Method of Sampling:	EN 932-1
Client Ref. No:	325294 - 40mm Grey	Sampled By:	Celtest
Date and Time of Sampling:	13/12/2023	Tested By:	EK
Date of Receipt at Lab:	14/12/2023		
Date of Start of Test:	15/12/2023		
Sampling Location:	ST 51		
Material Description	40mm Grey		

RESULTS: Were any unrepresentative lumps present? No



BS Test Sieve Size	Percentage By Mass Passing	Specification Limit
125.0 mm	100	
75.0 mm	100	
63.0 mm	100	
45.0 mm	99	
40.0 mm	95	
31.5 mm	45	
22.4 mm	14	
20.0 mm	9	
16.0 mm	5	
14.0 mm	5	
11.2 mm	4	
10.0 mm	4	
8.0 mm	4	
5.6 mm	4	
4.0 mm	4	
2.8 mm	4	
2.0 mm	4	
1.4 mm	3	
1.0 mm	3	
0.710 mm	3	
0.500 mm	3	
0.355 mm	2	
0.250 mm	2	
0.180 mm	1	
0.125 mm	1	
0.090 mm	1	
0.063 mm	1.3	

This test report shall not be reproduced, except in full, without the written approval of Celtest Company Limited.

These results relate only to the items tested.

Comments:

None

Report checked and approved by:

Euros Jones
 Technical Manager