


**GRADATION ANALYSIS TEST REPORT**

Product: 6.3/14mm  
 Material Code: 614  
 Supplied by: Dow low Quarry  
 Customer:  
 Site Address:  
 Material type: BS EN 12620 / Limestone



Sampled to: BS EN 932- 1: 1997  
 Prepared to: BS EN 932- 2: 1999  
 Test method: BS EN 933- 1: 2012

Sample number	1147
Ticket No	
Sampled by	
Date Sampled	14/03/2019
Sample location	Aggregate Plant
Weather Conditions	



Sieve Size (mm)	Percent passing	Specification	Complies (Spec)	Control limits	Complies (Ctrl)
31.5	100	100 - 100	Yes	-	-
25	100	-	-	-	-
20	100	98 - 100	Yes	-	-
16	100	-	-	-	-
14	99	85 - 100	Yes	-	-
12.5	87	-	-	-	-
10	12	-	-	-	-
8	1	-	-	-	-
6.3	0	0 - 20	Yes	-	-
5	0	-	-	-	-
4	0	-	-	-	-
2.8	0	0 - 5	Yes	-	-
0.063	0.1	0 - 4.0	Yes	-	-
Uniformity Coefficient	1				

Sampled By:

Tested By:

Date Tested:

15/03/2019